

APPLICATION UNDER UNITED STATES PATENT LAWS

Atty. Dkt. No. PW 279213
(M#)

Invention: PERPENDICULAR MAGNETIC RECORDING MEDIUM

Inventor (s): OIKAWA et al.

Pillsbury Winthrop LLP
Intellectual Property Group
1100 New York Avenue, NW
Ninth Floor
Washington, DC 20005-3918
Attorneys
Telephone: (202) 861-3000

This is a:

- ☐ Provisional Application
- ☒ Regular Utility Application
- ☐ Continuing Application
 - ☒ The contents of the parent are incorporated by reference
- ☐ PCT National Phase Application
- ☐ Design Application
- ☐ Reissue Application
- ☐ Plant Application
- ☐ Substitute Specification
 - Sub. Spec Filed _____
 - in App. No. _____ / _____
- ☐ Marked up Specification re
 - Sub. Spec. filed _____
 - In App. No _____ / _____

SPECIFICATION

TITLE OF THE INVENTION

PERPENDICULAR MAGNETIC RECORDING MEDIUM

CROSS-REFERENCE TO RELATED APPLICATIONS

5 This application is based upon and claims the benefit of priority from the prior Japanese Patent Application No. 2000-287720, filed September 21, 2000, the entire contents of which are incorporated herein by reference.

BACKGROUND OF THE INVENTION

10 The present invention relates to a perpendicular magnetic recording medium, particularly, to a perpendicular magnetic recording medium comprising a ferromagnetic magnetic recording layer containing cobalt.

15 In a perpendicular magnetic recording system, information is recorded by magnetization in the direction perpendicular to the recording medium surface. Compared with the areal magnetic recording system, the perpendicular magnetic recording system is
20 low in demagnetizing field within each bit in performing a high density recording and, thus, is adapted for the improvement in the areal recording density.

Also, the perpendicular magnetic recording medium,
25 in which a soft magnetic layer is arranged between the substrate and the perpendicular magnetic recording layer, performs the function of a so-called

"perpendicular double layered medium". The soft magnetic layer acts as the flux path to assist the recording magnetic field in refluxing between the magnetic head and the recording medium so as to improve the recording-reproducing efficiency. A cobalt-based material such as a CoCr alloy, a CoPt alloy or CoCrPt alloy is used in the perpendicular magnetic recording layer. Cobalt has a hexagonal close-packed structure (hcp structure). When a thin film of Co is formed, the easy magnetization axis of cobalt tends to be oriented in a direction perpendicular to the film surface. Therefore, Co is adapted for use in the preparation of a perpendicular magnetic recording layer.

In order to improve the magnetic recording characteristics, it is necessary to improve the perpendicular magnetic anisotropy of the Co-based recording layer and to promote the fineness of the crystal grains in the Co-based recording layer, thereby improving the coercive force and magnetostatic characteristics such as a perpendicular squareness ratio. To this end, known is a method that a nonmagnetic under layer such as a Ti layer is formed between a CoCr-based recording layer and a nonmagnetic substrate. This method is effective for improving the perpendicular orientation of the perpendicular magnetic recording layer. As described above, in the case of arranging a soft magnetic layer, the perpendicular

orientation of the Co-based magnetic recording layer is rendered poorer than in the case where the Co-based magnetic recording layer is formed in direct contact with the nonmagnetic substrate. It is possible to
5 improve the perpendicular orientation of the magnetic recording layer by arranging an under layer such as a Ti layer between the soft magnetic layer and the magnetic recording layer in this case, too. However, for further improving the recording density, required
10 is a nonmagnetic under layer that permit obtaining a higher orientation.

On the other hand, it was most popular in the past to use a material containing Co and Cr as main components for forming the perpendicular magnetic
15 recording layer. It should be noted in this connection that Cr is segregated in the crystal grain boundary in the material containing Co and Cr as main components, making it possible to obtain a magnetic recording medium having a high coercive force and a high signal
20 to noise ratio. However, it was impossible to obtain a sufficient perpendicular magnetic anisotropy by simply adding, for example, traces of Ta to the CoCr recording layer. On the other hand, a CoPt alloy recording layer exhibits a magnetic anisotropy larger than that
25 exhibited by the elemental Co, though it is difficult to obtain a large coercive force and a high S/N ratio because Pt is not segregated in the grain boundary in

the case of the CoPt alloy recording layer. Such being the situation, it has been clarified that, in the recording layer prepared by adding Pt to the CoCr alloy, it is possible to obtain magnetic recording characteristics more excellent than those of the CoCr recording layer. A CoPtO recording layer prepared by adding oxygen to a CoPt magnetic layer is proposed in, for example, Japanese Patent Disclosure (Kokai) No. 7-235034, which corresponds to U.S. Patent No. 5,792,564, as a means for improving the magnetic recording characteristics of the magnetic recording layer. It is taught in the prior art that it is possible to prepare a magnetic recording medium exhibiting high perpendicular anisotropy and coercive force and satisfactory in the S/N ratio by forming a grain boundary layer rich in oxygen. A quite different method utilizing a multi-layered film consisting of a combination of Co and, for example, Pd has also been found. To be more specific, it has been found that a very high perpendicular anisotropy can be obtained by utilizing the interfacial magnetic anisotropy generated at the interface between Co and Pd. It has also been found that the S/N ratio can be improved to some extent by forming a segregation structure by, for example, an oxygen addition. However, since the matching of the lattice constant between Co and Pd or Pt is insufficient, the crystallinity of the multi-layered

film was not sufficiently high.

As described above, various combinations between the Co-based alloy and the materials of the under layer have been found in respect of the perpendicular magnetic recording medium using a Co-based alloy magnetic recording layer. However, further improvements are required for obtaining a perpendicular magnetic recording medium capable of exhibiting a satisfactory perpendicular anisotropy and a good S/N ratio and also capable of realizing a higher coercive force and a higher reproducing output.

The crystal orientation and the crystal grain diameter of the magnetic recording layer are greatly dependent on the surface state of the substrate. Therefore, even where a nonmagnetic under layer is applied, it is necessary to control the surface state of the substrate for further improving the perpendicular orientation the recording layer. Where, for example, Ti is used for forming the under layer, it is taught in, for example, Japanese Patent Disclosure No. 6-58734 that it is possible to obtain a surface state of the under layer, which can be perpendicularly oriented easily, by further forming a nonmagnetic layer made of Si, Ge or Sn between the substrate and the Ti under layer. It is described in the prior art quoted above that it is effective to form the nonmagnetic under layer of the double-layered structure between

a soft magnetic layer and a Co-based recording layer in a perpendicular double layered film. However, for further improving the recording density, it is required to develop a nonmagnetic under layer capable of obtaining a further improved orientation. Under the circumstances, various studies are being made in an attempt to arrive at new materials of the under layer and the combination of laminations of the under layers in each of the cases where a soft magnetic layer is arranged and not arranged between the under layer and the substrate. However, sufficient magnetic recording characteristics capable of fully coping with the demands for the further improvement of the recording density in the future have not yet been obtained when it comes to the nonmagnetic under layers published to date.

BRIEF SUMMARY OF THE INVENTION

An object of the present invention, which has been achieved in view of the situation described above, is to provide a magnetic recording medium capable of exhibiting a high coercive force and obtaining a high reproducing output by improving the perpendicular orientation of the Co-based magnetic recording layer.

According to a first aspect of the present invention, there is provided a perpendicular magnetic recording medium, comprising a nonmagnetic substrate, a first under layer formed on the nonmagnetic substrate

and containing iron, a second under layer formed on the first under layer and containing mainly ruthenium, and a magnetic recording layer formed on the second under layer and containing mainly cobalt.

5 According to a second aspect of the present invention, there is provided a perpendicular magnetic recording medium, comprising a nonmagnetic substrate, a first under layer formed on the nonmagnetic substrate and containing cobalt, a second under layer formed on
10 the first under layer and containing mainly ruthenium, and a magnetic recording layer formed on the second under layer and containing mainly cobalt.

 According to a third aspect of the present invention, there is provided a perpendicular magnetic
15 recording medium, comprising a nonmagnetic substrate, a first under layer formed on the nonmagnetic substrate and containing mainly ruthenium, a second under layer formed on the first under layer and containing mainly cobalt, and a magnetic recording layer formed on the
20 second under layer and containing mainly cobalt.

 According to a fourth aspect of the present invention, there is provided a perpendicular magnetic recording medium, comprising a nonmagnetic substrate, a first under layer formed on the nonmagnetic substrate
25 and containing titanium, a second under layer formed on the first under layer and containing mainly ruthenium, and a magnetic recording layer formed on the second

under layer and containing mainly cobalt.

According to a fifth aspect of the present invention, there is provided a perpendicular magnetic recording medium, comprising a nonmagnetic substrate, a soft magnetic layer formed on the nonmagnetic substrate, a first under layer formed on the soft magnetic layer and containing as a main component at least one of vanadium and chromium, a second under layer formed on the first under layer and containing mainly ruthenium, and a magnetic recording layer formed on the second under layer and containing mainly cobalt.

According to a sixth aspect of the present invention, there is provided a perpendicular magnetic recording medium, comprising a nonmagnetic substrate, and a magnetic recording layer formed on the nonmagnetic substrate and having a multi-layered structure prepared by alternately laminating a ferromagnetic layer containing mainly cobalt and a nonmagnetic layer containing mainly ruthenium.

According to the present invention, a perpendicular magnetic recording medium having a high coercive force and a high reproducing output can be obtained by disposing a nonmagnetic layer containing mainly ruthenium somewhere in the perpendicular magnetic recording medium. Such a non magnetic layer containing mainly ruthenium can be formed as a first under layer, and a layer containing another

suitable element is formed as a second under layer.

Alternatively, a layer containing another suitable element is formed as a first under layer, and such a nonmagnetic layer containing mainly ruthenium

5 is formed as a second under layer in the perpendicular magnetic recording medium of the present invention.

Further, it is also possible to form a multi-layered magnetic recording layer by alternately laminating a Co-based magnetic layer and such Ru-based nonmagnetic
10 layer so as to enable the perpendicular magnetic recording medium of the present invention to exhibit a high coercive force and a high reproducing output.

Additional objects and advantages of the invention will be set forth in the description which follows, and
15 in part will be obvious from the description, or may be learned by practice of the invention. The objects and advantages of the invention may be realized and obtained by means of the instrumentalities and combinations particularly pointed out hereinafter.

20 BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWING

The accompanying drawings, which are incorporated in and constitute a part of the specification, illustrate presently preferred embodiments of the invention, and together with the general description given above
25 and the detailed description of the preferred embodiments given below, serve to explain the principles of the invention.

FIG. 1 schematically shows the construction of an example of a magnetic recording medium of the present invention;

FIG. 2 schematically shows the construction of another example of a magnetic recording medium of the present invention;

FIG. 3 schematically shows the construction of still another example of a magnetic recording medium of the present invention; and

FIG. 4 is a view showing the construction of an example of the magnetic recording apparatus in which the magnetic recording medium of the present invention can be applied.

DETAILED DESCRIPTION OF THE INVENTION

The perpendicular magnetic recording medium of the present invention comprises a nonmagnetic substrate and a Co-based perpendicular magnetic recording layer, and the present invention can be roughly classified into some types on the basis of the five view points described below.

In the perpendicular magnetic recording medium according to the first to fourth view points of the present invention, a first underlying and a second under layer are formed in the order mentioned between the nonmagnetic substrate and a Co-based perpendicular magnetic recording layer. Any one of the first, second under layers, contains ruthenium. The perpendicular

magnetic recording medium according to the first to fourth view points of the present invention is characterized as follows by the laminate structure consisting of a nonmagnetic layer containing ruthenium, a layer containing another element, and a Co-based perpendicular magnetic recording layer.

The first type of the present invention provides a perpendicular magnetic recording medium, comprising a nonmagnetic substrate, a first under layer formed on the nonmagnetic substrate and containing iron, a second under layer formed on the first under layer and containing mainly ruthenium, and a magnetic recording layer formed on the second under layer and containing mainly cobalt.

According to a preferred embodiment of the first type of the present invention, the first under layer consists essentially of iron. Alternatively, the first under layer contains iron as a main component and at least one element selected from the group consisting of aluminum, silicon, tantalum, carbon, zirconium, nitrogen and cobalt as an auxiliary component.

According to the first type of the present invention, it is possible to improve the perpendicular orienting properties and magnetic characteristics of a perpendicular magnetic recording medium having a Co-based, such as a CoPtO-based alloy by using an under layer of a laminate structure comprising a first

under layer consisting essentially of iron or
containing iron as a main component and, preferably,
a body-centered cubic crystal material described above,
as an auxiliary component, and a second under layer
5 containing ruthenium of a hexagonal close-packed
structure. This construction is effective for ensuring
a fineness and an uniformity of a crystal diameter in
addition to an improvement of a crystal orientation in
regard to the second under layer, therefore a fineness
10 and an uniformity of a crystal diameter is promoted in
addition to an improvement of a perpendicular crystal
orientation in regard to the Co-based magnetic
recording layer so as to decrease a transition noise
and improve a recording resolution of the recording
15 medium.

Preferred combinations of the main component and
the auxiliary component include the combination of
iron, tantalum and carbon, the combination of iron,
zirconium and nitrogen, the combination of iron and
20 cobalt, and the combination iron, aluminum and silicon.
The iron alloy containing not higher than 10 atomic %
of at least one of aluminum and silicon is called,
for example, Sendust.

These preferred combinations are soft magnetic
25 alloys having a high magnetic permeability.

Conventional Sendust, which is an iron alloy
containing 5% of aluminum, 10% of silicon and the

remaining part 85% of iron, has a basic crystal structure equal to that of iron. A soft magnetic material having a high permeability can be obtained by adding Al and Si to an iron alloy. Even if the characteristics as a soft magnetic material are changed by the change of the addition amount within a range within which the basic crystal structure is not changed, the resultant medium can be expected to produce the similar effect.

In the second type of the present invention, the first under layer contains cobalt as a main component, and the second under layer contains ruthenium as a main component.

According to the second type of the present invention, the under layer is formed of a material of a hexagonal close-packed structure or an amorphous material containing cobalt as a main component. Also, the second under layer, which is laminated on the first under layer, is formed of ruthenium of a hexagonal close-packed structure. The particular construction of the under layers permits improving the perpendicular orienting properties and the magnetic properties of the perpendicular magnetic recording medium comprising a Co-based magnetic layer, particularly, a CoPtO-based magnetic layer. This construction is effective for ensuring a fineness and an uniformity of a crystal diameter in addition to an improvement of a crystal

orientation in regard to the second under layer,
therefore a fineness and an uniformity of a crystal
diameter is promoted in addition to an improvement of
a perpendicular crystal orientation in regard to
5 the Co-based magnetic recording layer so as to decrease
a transition noise and improve a recording resolution
of the recording medium.

In the preferred embodiment of the second type of
the present invention, it is desirable for the first
10 under layer to contain at least one auxiliary component
selected from the group consisting of zirconium,
niobium and chromium. Also, the preferred combinations
of the main component and the auxiliary component
includes a combination of cobalt, zirconium and niobium
15 and a combination of cobalt and chromium. It is
desirable for the alloy containing cobalt and chromium
not to exhibit ferromagnetism. Also, the combination
of cobalt, zirconium and niobium forms a soft magnetic
alloy having a high magnetic permeability.

20 It is possible to use a soft magnetic alloy having
a high permeability such as a CoZr-based alloy like
CoZrNb, an FeCo-based alloy, an FeSi-based alloy,
an FeTaC, FeZrN and NiFe-based alloy like Permalloy
for forming a soft magnetic layer that is interposed
25 between the nonmagnetic substrate and the perpendicular
magnetic recording layer like the first under layer
used in each of the first and second types of

the present invention.

The perpendicular magnetic recording medium using the particular soft magnetic material having a high magnetic permeability, which performs the function of a so-called "double layered perpendicular medium", performs a part of the function of the magnetic head that the recording magnetic field from the magnetic head is refluxed and is expected to produce excellent recording/reading characteristics interaction. Even in the case of using such a soft magnetic layer, the perpendicular orienting effect is considered to be substantially the same by applying an under layer of a laminate structure to the perpendicular magnetic recording layer.

In the third type of the present invention, the first under layer contains ruthenium as a main component, and the second under layer contains cobalt as a main component.

In the third type of the present invention, it is desirable for the second under layer to contain chromium as an auxiliary component. In this case, it is desirable for the cobalt-chromium alloy not to exhibit ferromagnetism.

Also, it is desirable for the first under layer to consist essentially of ruthenium.

According to the third type of the present invention, the first under layer is formed of

a material containing ruthenium of a hexagonal close-packed structure as a main component. Also, the second under layer, which is laminated on the first under layer, is formed of a material of a hexagonal close-packed structure containing cobalt as a main component. The particular construction makes it possible to improve the perpendicular orienting properties and the magnetic properties of the perpendicular magnetic recording medium comprising a Co-based magnetic layer, particularly, a CoPtO-based magnetic layer. This construction is effective for ensuring a fineness and an uniformity of a crystal diameter in addition to an improvement of a crystal orientation in regard to the second under layer, therefore a fineness and an uniformity of a crystal diameter is promoted in addition to an improvement of a perpendicular crystal orientation in regard to the Co-based magnetic recording layer so as to decrease a transition noise and improve a recording resolution of the recording medium.

According to the fourth type of the present invention, employed is a laminate structure formed on the substrate and comprising a first under layer containing titanium as a main component, a second under layer containing ruthenium as a main component and a perpendicular magnetic recording layer containing cobalt.

The nonmagnetic layer containing titanium, which is a material of a hexagonal close-packed structure and used as a first under layer, is formed of, for example, titanium or a compound selected from the group
5 consisting of a nitride, a carbide and an oxide of titanium. It is also possible to use a titanium chromium alloy.

It is possible to form, for example, TiN having a NaCl structure by the sputtering of a TiN target
10 under an argon gas atmosphere. Titanium and nitrogen are not necessarily bonded to each other at a ratio of 1:1 on the substrate, and it is considered that a nitride having a partially different ratio is formed. Further, substantially the same effect can be obtained
15 in the case of forming an under layer formed of titanium alone. The similar effect on an improvement of a perpendicular orientation can be obtained in the cases where the under layer is formed of not only TiN but also a nitride having a different ratio and where a
20 nitride and titanium are present together in the under layer. Further, the similar effect can be expected in respect of the carbide and oxide of titanium.

The chromium addition amount in TiCr suitable for the first under layer is not higher than 10 atomic %.
25 Since titanium and chromium do not form a solid solution under room temperature, the basic crystal structure is similar to that of Ti and, thus, the

similar effect can be obtained sufficiently.

A layer containing ruthenium is used as the second under layer.

According to the present invention, a first under
5 layer consisting of a specified nonmagnetic or soft
magnetic material, a second under layer consisting of a
specified nonmagnetic material, and a layer consisting
of a ferromagnetic Co-based alloy material are formed
on the substrate, thereby making the Co-based alloy
10 layer, particularly, a CoPtO ferromagnetic layer having
an excellent perpendicular orientation. As a result,
it is possible to obtain a magnetic recording medium
exhibiting a high coercive force and a high reproducing
output.

15 Also, according to the present invention, it is
possible to arrange a soft magnetic layer between the
perpendicular magnetic recording medium relating to the
first to fourth view points and the first under layer.

It should be noted in respect of the effects
20 produced by the soft magnetic layer that the presence
of the soft magnetic layer permits the resultant
magnetic recording medium to perform the function of
a perpendicular double layered medium and that the
magnetic recording layer is enabled to produce
25 excellent recording-reproducing characteristics by the
interactive between the head and the soft magnetic
layer.

Examples of the materials forming the soft magnetic layer include Sendust, Permalloy, ferrite, FeGaGe, FeGeSi, FeAlGa, FeRuGaSi, FeSi, FeCoNi, FeSiB, FeNiPb, FeSiC, FeCuNbSiB, FeZrB, FeZrBCu, CoFeSiB, CoZrTa, and CoTi.

According to the fourth type of the present invention, the presence of the soft magnetic layer with the Co-based alloy magnetic recording layer permits the resultant magnetic recording medium to produce the effect of a double layered medium, and it is possible to obtain the Co-based alloy magnetic recording layer, particularly, a CoPtO alloy layer, exhibiting excellent perpendicular orientation. As a result, it is possible to obtain a magnetic recording medium exhibiting a high coercive force and a high reproducing output.

According to the fifth type of the present invention, there is provided a perpendicular magnetic recording medium, comprising a nonmagnetic substrate, a soft magnetic layer formed on the nonmagnetic substrate, a first under layer formed on the soft magnetic layer, a second under layer formed on the first under layer and containing ruthenium, and a magnetic recording layer formed on the second under layer and containing mainly cobalt, wherein the first under layer contains mainly at least one of the vanadium and chromium and is capable of optionally containing iron.

The produced effect and the preferred examples of the soft magnetic layer used are similar to those described previously.

According to the fifth type of the present invention, the presence of the soft magnetic layer with the Co-based alloy magnetic recording layer permits the resultant magnetic recording medium to produce the effect of a double layered medium, and it is possible to obtain the Co-based alloy magnetic recording layer, particularly, a CoPtO alloy layer, exhibiting excellent perpendicular orientation. As a result, it is possible to obtain a magnetic recording medium exhibiting a high coercive force and a high reproducing output.

It is desirable to use vanadium or chromium for forming the first under layer.

In the perpendicular magnetic recording medium according to the first to fifth types of the present invention, the material of the magnetic recording layer is not limited to the CoPtO alloy system. It is also possible for the magnetic recording layer to be formed of a CoCrPt-based alloy, or a multi-layered film system consisting of a Co film and a Pt film, consisting of a Co film and a Pd film or consisting of a Co film and a Ru film. The similar effect can be obtained even in the case where the film also contains oxygen. Also, the film containing ruthenium, which is used in the perpendicular magnetic recording medium according to

the first to fifth types of the present invention, consists essentially of ruthenium. However, it is possible to add another element such as Cr or Co to the film containing ruthenium.

5 According to the first to fifth types of the present invention, an appropriate combination of a layer containing ruthenium and another layer containing another element is used as the first and second under layers, and the particular combination is laminated
10 below the perpendicular magnetic recording layer. As a result, the crystal orientation of the second under layer is improved by the first under layer. In addition, the crystal grains are made finer and uniform in the second under layer. Also, since the
15 perpendicular magnetic recording layer is formed on the second under layer, the perpendicular orientation of the recording layer is improved by the presence of the second under layer. In addition, the crystal grains are microcrystallized and made uniform in the
20 perpendicular magnetic recording layer. It follows that it is possible to suppress the transition noise of the recording medium and to improve the recording resolution of the recording medium.

 Further, in order to prevent the under layer
25 formed on the soft magnetic layer from being affected by the crystal orientation and the crystal grain diameter in the soft magnetic layer, it is possible to

form an amorphous material layer made of, for example, carbon on the soft magnetic layer.

It is also possible to form an antiferromagnetic layer such as an FeMn layer or an antimagnetic layer
5 such as a CoSm layer between the non magnetic substrate and the soft magnetic layer to form an axis of a soft magnetic layer be uniform in the direction of circumference or radius.

According to the sixth type of the present
10 invention, used is a multi-layered perpendicular magnetic recording layer having a multi-layered structure consisting of a Co-based magnetic layer and a Ru-based nonmagnetic layer that are alternately laminated one upon the other. The recording layer
15 having the particular multi-layered structure permits further improving the perpendicular orientation and the perpendicular coercive force.

Also, according to the present invention, the multi-layered perpendicular magnetic recording layer
20 can be used as the perpendicular magnetic recording layer according to the first to fifth view points of the present invention.

FIG. 1 shows an example of the construction of a magnetic recording medium 10 of the present
25 invention. As shown in the drawing, the magnetic recording medium 10 comprises a substrate 1, a first under layer 2 formed on the substrate 1, a second under

layer 3 formed on the first under layer 2, a Co-based
ferromagnetic layer 4 made of, for example, a CoPtO
alloy and formed on the second under layer 3,
and a protective layer 5 formed on the ferromagnetic
layer 4.

Each of the layers laminate on the substrate 1 can
be formed by a sputtering method with the materials of
these layers used as targets.

FIG. 2 shows the construction of another example
of a magnetic recording medium of the present
invention. As shown in the drawing, the magnetic
recording medium 20 shown in FIG. 2 is substantially
equal in construction to the magnetic recording medium
10 shown in FIG. 1, except that a laminate structure
comprising a magnetic layer 4a, another magnetic layer
4b and a nonmagnetic layer 6 made of ruthenium and
interposed between the magnetic layers 4a and 4b is
formed in place of the magnetic layer 4 shown in
FIG. 1. Preferably, the nonmagnetic layer 6 should
consist essentially of ruthenium. Where the magnetic
layer is of a multi-layer structure constructed such
that a nonmagnetic layer containing ruthenium as a main
component, which is a nonmagnetic intermediate layer,
is sandwiched between two adjacent ferromagnetic
layers, it is possible to further improve the
perpendicular orienting properties and the magnetic
properties of the magnetic layer.

FIG. 3 is a cross sectional view showing still another example of the construction of a magnetic recording medium 30 of the present invention. As shown in the drawing, the magnetic recording medium 30 shown in FIG. 3 is substantially equal in construction to the magnetic recording medium 10 shown in FIG. 1, except that a soft magnetic layer 7 is interposed between the substrate 1 and the first under layer 2 in the magnetic recording medium 30 shown in FIG. 3. The presence of the soft magnetic layer 7 permits the resultant magnetic recording medium 30 to perform the function of a double layered perpendicular film, and the magnetic recording medium 30 is expected to produce excellent recording/reading characteristics because of the interact between the head and the soft magnetic layer.

The present invention will now be described more in detail with reference the Examples which follow.

Example 1:

A glass substrate meeting the standard specification of a 2.5 inch magnetic disc was prepared as a nonmagnetic substrate. Each of the under layers, the magnetic layer, etc. was formed as described below on the glass substrate by means of DC magnetron sputtering.

In the first step, a iron layer was formed on the glass substrate as a first under layer in

a thickness of about 50 nm. Then, a ruthenium layer was formed as a second under layer on the iron layer in a thickness of about 37 nm.

5 In the next step, a CoPtCrO magnetic layer was formed on the second under layer by means of a sputtering of a CoPtCr alloy target under an argon atmosphere containing traces of O₂. Incidentally, the CoPtCr alloy target contained 20 atomic % of Pt, 16 atomic % of Cr and the balance of Co. In this case, 10 used was a CoPtCr target having a relatively high Cr concentration. However, if the Cr concentration is not higher than 16 atomic %, an essential change in the construction of the magnetic layer is scarcely brought about by the Cr addition, making it possible to obtain 15 the similar effect as the characteristics of the medium.

Finally, a carbon layer having 10 nm of thickness was laminated as a protective layer on the magnetic layer so as to obtain a desired magnetic recording 20 medium.

The magnetic characteristics of the resultant magnetic recording medium were measured by a vibrating sample type magnetometer (VSM), with the results as shown in Table 1. The mark "Hc⊥" in Table 1 25 represents a coercive force in the case where a magnetic field is applied in a direction perpendicular to the film surface. Also, the mark "Hc//" in Table 1

represents a coercive force in the case where a magnetic field is applied to in a areal direction of the film surface. Further, the perpendicular squareness ratio represents a ratio of the residual magnetization to the saturated magnetization in the case of applying a magnetic field in a perpendicular direction.

Example 2:

A magnetic recording medium was prepared as in Example 1, except that a FeTaC layer having a thickness of about 100 nm was formed in place of the Fe layer. The FeTaC layer was formed by sputtering a FeTaC target containing 10 atomic % of Ta, 10 atomic % of C and the balance of Fe under an argon atmosphere. The magnetic properties of the magnetic recording medium thus obtained were measured as in Example 1, with the results as shown in Table 1.

Example 3:

A magnetic recording medium was prepared as in Example 1, except that a FeZrN layer having a thickness of about 100 nm was formed in place of the Fe layer. The FeZrN layer was formed by sputtering a FeZrN target containing 10 atomic % of Zr, 10 atomic % of N and the balance of Fe under an argon atmosphere. The magnetic properties of the magnetic recording medium thus obtained were measured as in Example 1, with the results as shown in Table 1.

Example 4:

A magnetic recording medium was prepared as in Example 1, except that a FeCo layer having a thickness of about 50 nm was formed in place of the Fe layer.

5 The FeCo layer was formed by sputtering a FeCo target containing 50 atomic % of Fe and the balance of Co under an argon atmosphere. The magnetic properties of the magnetic recording medium thus obtained were measured as in Example 1, with the results as shown in
10 Table 1.

Example 5:

A magnetic recording medium was prepared as in Example 1, except that a CoZrNb layer having a thickness of about 100 nm was formed in place of
15 the Fe layer. The CoZrNb layer was formed by sputtering a CoZrNb target containing 5 atomic % of Zr, 10 atomic % of Nb and the balance of Co under an argon atmosphere. The magnetic properties of the magnetic recording medium thus obtained were measured as in
20 Example 1, with the results as shown in Table 1.

Example 6:

A magnetic recording medium was prepared as in Example 1, except that a Co layer having a thickness of about 75 nm was formed in place of the Fe layer.

25 The magnetic properties of the magnetic recording medium thus obtained were measured as in Example 1, with the results as shown in Table 1.

Example 7:

A magnetic recording medium was prepared as in Example 1, except that a CoCr layer having a thickness of about 40 nm was formed in place of the Fe layer.

5 The CoCr layer was formed by sputtering a CoCr target containing 33 atomic % of Cr and the balance of Co under an argon atmosphere. The magnetic properties of the magnetic recording medium thus obtained were measured as in Example 1, with the results as shown in
10 Table 1.

Example 8:

A magnetic recording medium was prepared as in Example 1, except that a ruthenium layer having a thickness of about 20 nm was formed as the first
15 under layer in place of the Fe layer, and a CoCr layer having a thickness of about 15 nm was formed as the second under layer in place of the ruthenium layer. The CoCr layer was formed by sputtering a CoCr target containing 33 atomic % of Cr and the balance of Co
20 under an argon atmosphere. The magnetic properties of the magnetic recording medium thus obtained were measured as in Example 1, with the results as shown in Table 1.

Comparative Example 1:

25 A magnetic recording medium was prepared as in Example 1, except that a Cr layer having a thickness of about 40 nm was formed in place of the Fe layer,

and the second under layer was not formed. The magnetic properties of the magnetic recording medium thus obtained were measured as in Example 1, with the results as shown in Table 1.

5 Comparative Example 2:

A magnetic recording medium was prepared as in Example 1, except that the second under layer was not formed. The magnetic properties of the magnetic recording medium thus obtained were measured as in
10 Example 1, with the results as shown in Table 1.

Comparative Example 3:

A magnetic recording medium was prepared as in Example 2, except that the second under layer was not formed. The magnetic properties of the magnetic
15 recording medium thus obtained were measured as in Example 1, with the results as shown in Table 1.

Comparative Example 4:

A magnetic recording medium was prepared as in Example 3, except that the second under layer was not
20 formed. The magnetic properties of the magnetic recording medium thus obtained were measured as in Example 1, with the results as shown in Table 1.

Comparative Example 5:

A magnetic recording medium was prepared as in
25 Example 4, except that the second under layer was not formed. The magnetic properties of the magnetic recording medium thus obtained were measured as in

Example 1, with the results as shown in Table 1.

Comparative Example 6:

5 A magnetic recording medium was prepared as in
Example 5, except that the second under layer was not
formed. The magnetic properties of the magnetic
recording medium thus obtained were measured as in
Example 1, with the results as shown in Table 1.

Comparative Example 7:

10 A magnetic recording medium was prepared as in
Example 6, except that the second under layer was not
formed. The magnetic properties of the magnetic
recording medium thus obtained were measured as in
Example 1, with the results as shown in Table 1.

Comparative Example 8:

15 A magnetic recording medium was prepared as in
Example 7, except that the second under layer was not
formed. The magnetic properties of the magnetic
recording medium thus obtained were measured as in
Example 1, with the results as shown in Table 1.

20 Comparative Example 9:

25 A magnetic recording medium was prepared as in
Example 8, except that the second under layer was not
formed. The magnetic properties of the magnetic
recording medium thus obtained were measured as in
Example 1, with the results as shown in Table 1.

Where the magnetic recording medium including
a soft magnetic layer in addition to the recording

5

Table 1

	Underlying layer	Hc _⊥ (A/m)	Hc _{//} (A/m)	Hc _⊥ /Hc _{//}	Perpendicular squareness ratio
Example 1	Fe/Ru	222780	103490	2.15	0.97
Example 2	FeTaC/Ru	244110	106650	2.29	0.99
Example 3	FeZrN/Ru	240160	105860	2.27	0.98
Example 4	FeCo/Ru	249640	108230	2.31	1.00
Example 5	CoZrNb/Ru	209350	115340	1.82	0.97
Example 6	Co/Ru	263070	96380	2.73	1.00
Example 7	CoCr/Ru	271760	97960	2.77	0.99
Example 8	Ru/CoCr	269390	94800	2.84	0.98
Comparative Example 1	Cr	83740	229100	0.37	0.15
Comparative Example 2	Fe	27650	18960	1.32	0.02
Comparative Example 3	FeTaC	15010	15800	0.95	0.01
Comparative Example 4	FeZrN	14220	12640	1.13	0.01
Comparative Example 5	FeCo	16590	13430	1.24	0.02
Comparative Example 6	CoZrNb	13430	15800	0.85	0.01
Comparative Example 7	Co	33970	25280	1.34	0.05
Comparative Example 8	CoCr	180120	117710	1.53	0.99
Comparative Example 9	Ru	199080	131930	1.51	0.85

A perpendicular orientation is improved with increase in the ratio $H_{c\perp}/H_{c//}$ shown in Table 1, and an read output is increased in the case where the perpendicular squareness ratio shown in Table 1 is as close to 1 as possible so as to provide an excellent perpendicular magnetic recording medium. In each of Comparative Example 1, the ratio $H_{c\perp}/H_{c//}$ was smaller than 1, and the perpendicular squareness ratio was small, indicating that a areal orientation was formed in each of these Comparative Examples. Also, in each of Comparative Examples 2 to 7, the $H_{c\perp}$, $H_{c//}$ and perpendicular squareness ratio were more smaller the media have approximately complete areal orientation. This is because the soft magnetic layer is not partitioned magnetically with the recording layer so that the properties of the soft magnetic layer having high magnetic moment is predominant. However the properties of the recording layer was not influenced to the whole properties, therefore it is found that the perpendicular orientation of the recording layer is weak, and the areal orientation thereof is strong. Comparative Examples 8 and 9, which were not sufficient in terms of the perpendicular orientation, exhibited the most satisfactory characteristics among the Comparative Examples.

On the other hand, any of the $H_{c\perp}/H_{c//}$ ratio and the perpendicular squareness ratio in any of Examples 1

to 9 of the present invention was found to be higher than that for any of Comparative Examples 8 and 9. In addition, the squareness ratio was substantially 1 in any of the Examples of the present invention.

5 These clearly support that the characteristics of the perpendicular magnetic recording medium are markedly improved in the present invention. The experimental data clearly support that, an under layer, which fails to exhibit a sufficient perpendicular
10 orientation when used singly, produces the effect of improving the crystallinity of ruthenium when the under layer is used in combination with another under layer containing ruthenium as a main component. In this fashion, the present invention permits obtaining
15 a Co-based magnetic layer exhibiting excellent perpendicular orienting properties, making it possible to obtain a perpendicular magnetic recording medium exhibiting satisfactory characteristics including a high coercive force and a high read output.

20 Example 9:

A magnetic recording medium was obtained as in Example 1, except that a Ti layer having a thickness of about 40 nm was formed as the first under layer in place of the Fe layer. The magnetic characteristics of
25 the magnetic recording medium thus obtained were measured as in Example 1. Table 2 shows the results.

Example 10:

A magnetic recording medium was obtained as in Example 1, except that a TiCr layer having a thickness of about 40 nm was formed as the first under layer in place of the Fe layer. The TiCr layer was formed by the sputtering of a target having a composition of Ti-Cr (10 at%) under an Ar gas atmosphere. The magnetic characteristics of the magnetic recording medium thus obtained were measured as in Example 1. Table 2 shows the results.

Example 11:

A magnetic recording medium was obtained as in Example 1, except that a TiN layer having a thickness of about 35 nm was formed as the first under layer in place of the Fe layer. The TiN layer was formed by the sputtering of a target having a composition of Ti-N 50 at% under an Ar gas atmosphere. The magnetic characteristics of the magnetic recording medium thus obtained were measured as in Example 1. Table 2 shows the results.

Example 12:

A magnetic recording medium was obtained as in Example 1, except that a Sendust layer having a thickness of about 30 nm was formed as the first under layer in place of the Fe layer. The Sendust layer was formed by the sputtering of a target having a composition of Fe 85 at%-Al 5 at%-Si 10 at% under an

Ar gas atmosphere. The magnetic characteristics of the magnetic recording medium thus obtained were measured as in Example 1. Table 2 shows the results.

Comparative Example 10:

5 A magnetic recording medium was obtained as in Example 9, except that a second under layer was not formed. The magnetic characteristics of the magnetic recording medium thus obtained were measured as in Example 1. Table 2 shows the results.

10 Comparative Example 11:

 A magnetic recording medium was obtained as in Example 10, except that a second under layer was not formed. The magnetic characteristics of the magnetic recording medium thus obtained were measured as in
15 Example 1. Table 2 shows the results.

Comparative Example 12:

 A magnetic recording medium was obtained as in Example 11, except that a second under layer was not formed. The magnetic characteristics of the magnetic
20 recording medium thus obtained were measured as in Example 1. Table 2 shows the results.

Comparative Example 13:

 A magnetic recording medium was obtained as in Example 1, except that a vanadium layer having a
25 thickness of 41 nm was formed as the first under layer in place the Fe layer, and that a second under layer was not formed. The magnetic characteristics of the

magnetic recording medium thus obtained were measured as in Example 1. Table 2 shows the results.

Comparative Example 14:

5 A magnetic recording medium was obtained as in Example 12, except that a second under layer was not formed. The magnetic characteristics of the magnetic recording medium thus obtained were measured as in Example 1. Table 2 shows the results.

Table 2

	Under layer	Hc \perp (A/m)	Hc \parallel (A/m)	Hc \perp /Hc \parallel	Perpendicular squareness ratio
Example 9	Ti/Ru	270970	93220	2.91	0.99
Example 10	TiCr/Ru	282030	99540	2.83	1.0
Example 11	TiN/Ru	273340	96380	2.84	0.98
Example 12	Sendust/Ru	203820	112970	1.80	0.96
Comparative Example 10	Ti	200660	166690	1.20	0.73
Comparative Example 11	TiCr	186440	165110	1.13	0.62
Comparative Example 12	TiN	86110	145360	0.59	0.18
Comparative Example 13	V	90850	226730	0.40	0.14
Comparative Example 14	Sendust	18170	15010	1.21	0.01

Where the magnetic recording medium including a soft magnetic layer in addition to the recording magnetic layer is measured by VSM, the resultant characteristics includes both of two characteristics relating to the soft magnetic layer and the magnetic recording layer. However since it is possible to interpret the characteristics separately in respect of Example 12, the values for the recording layer approximately alone are shown.

As apparent from Table 2, the value of $H_{c\perp}/H_{c//}$ for each of Comparative Examples 12 and 13 was not larger than 1, and the perpendicular squareness ratio was also small, supporting that a areal orientation was formed in each of these Comparative Examples. Also, in Comparative Example 14, the $H_{c\perp}$, $H_{c//}$ and perpendicular squareness ratio were more smaller the media have approximately complete areal orientation. This is because the soft magnetic layer is not partitioned magnetically with the recording layer so that the properties of the soft magnetic layer having high magnetic moment is predominant. However the properties of the recording layer was not influenced to the whole properties, therefore it is found that the perpendicular orientation of the recording layer is weak, and the areal orientation thereof is strong. A areal orientation was not recognized in each of Comparative Examples 10 and 11. However, the value of

Hc// was large, i.e., not smaller than 2 kOe, and the perpendicular squareness ratio was 0.6 to 0.7 in each of these Comparative Examples, supporting that the perpendicular orientation was insufficient.

5 As described above, both of Examples 8 and 9 of the present invention exhibited the values of $H_{c\perp}/H_{c//}$ and the perpendicular squareness ratio larger than those for Comparative Example 15, and the squareness ratio was substantially 1 in each of Examples 9-12 of
10 the present invention. These clearly support that the characteristics as the perpendicular magnetic recording medium were markedly improved in the present invention. This indicates that, where an under layer is formed under a Ru layer, it is possible to improve the
15 crystallinity of Ru, though when such an under layer is singly formed under the magnetic recording layer, the perpendicular orientation of the magnetic recording layer is insufficient. Such being the situation, it has been clarified that it is possible to obtain a
20 CoPtO-based magnetic layer exhibiting an excellent perpendicular orientation in the case where an under layer of a laminate structure is used as an under layer of the CoPtO-series magnetic layer, said laminate structure consisting of a first under layer made of Ti, TiCr, TiN, V or Sendust and formed on the substrate and
25 a second under layer formed on the first under layer and made of Ru. As a result, it is possible to obtain

a perpendicular magnetic recording medium having a high coercive force and exhibiting a high reproducing output.

5 In each of the Examples described above, a glass substrate was used as the nonmagnetic substrate. However, the similar effect can be obtained in the case where an Al-based alloy substrate, a Si single crystal substrate having an oxidized surface, or a substrate having, for example, NiP plated on the surface is used
10 as the nonmagnetic substrate. Also, the film formation was performed by a sputtering method in each of the Examples described above. However, it is also possible to employ other film formation methods such as a vacuum vapor deposition method, with substantially the same
15 effect.

Example 13:

A magnetic recording medium was obtained as in Example 1, except that a FeAlSi soft magnetic layer was formed on a substrate by sputtering a target having a
20 composition of Fe-5 at%-Al 10 at%-Si under an Ar gas atmosphere, and that a V layer having a thickness of 41 nm was formed as the first under layer in place of the Fe layer. The magnetic characteristics of the magnetic recording medium thus obtained were measured
25 as in Example 1. The other magnetic recording media were obtained and the magnetic characteristics of them were measured as the same way except that the

compositions were Fe 10 at%-Ta 10 at%-C, Fe 10 at%-Zr
10 at%-N, Fe 50 at%-Co, and Co 5 at% Zr 10 at%-Nb,
respectively. It has been found that the magnetic
recording media thus obtained were satisfactory in each
5 of the ratio of the perpendicular coercive force to the
areal coercive force and the perpendicular squareness
ratio.

Example 14:

A magnetic recording medium was obtained as in
10 Example 1, except that a Cr layer having a thickness of
about 40 nm was formed as the first under layer in
place of the Fe layer. The magnetic characteristics of
the magnetic recording medium thus obtained were
measured as in Example 1. It has been found that
15 the magnetic recording medium thus obtained was
satisfactory in each of the ratio of the perpendicular
coercive force to the areal coercive force and the
perpendicular squareness ratio.

Additional experiments were conducted in line with
20 Examples 1 to 14, except that alloy layers of RuCr and
RuCo were used in place of the Ru under layer, with
substantially the same improving effects.

Further, additional experiments were conducted by
using each of alloy layers of CoPt, CoCr and CoCrPt as
25 the magnetic recording layer in place of the CoPtO
recording layer, with substantially the same improving
effects.

Still further, additional experiments were conducted by using as a magnetic recording layer a multi-layered film of Co/Pd, Co/Pt or Co/Ru in place of the CoPtO recording layer, said multi-layered film being prepared by alternately laminating 20 times a Co layer having a thickness of about 0.3 nm and a Pd layer, a Pt layer or a Ru layer each having a thickness of about 1 nm, with substantially the same improving effects.

Example 15:

Perpendicular magnetic recording media were prepared as in Examples 1 to 14, except that perpendicular magnetic recording layers of a laminate structure were formed in place of each one CoPtO magnetic layer formed in Examples 1 to 14, said laminate structure being prepared by forming a first layer of a CoPtCrO magnetic layer having a thickness of 13 nm, followed by forming a Ru layer having a thickness of 4 nm as a nonmagnetic intermediate layer of the recording layer and subsequently forming again a second layer of a CoPtCrO magnetic layer. The magnetic characteristics of each of the magnetic recording media thus obtained were measured, with the result that the recording layer of the laminate structure was found to be superior to the recording layer of a single layer structure in each of $H_c \perp$ and $H_c \perp / H_c //$. The experimental data clearly support that

the perpendicular orientation and the perpendicular coercive force of the perpendicular magnetic recording medium can be improved by employing a perpendicular magnetic recording layer of a laminate structure and by
5 using a Ru layer as a nonmagnetic intermediate layer of the laminate structure.

Example 16:

Perpendicular magnetic recording media were prepared as in Examples 1 to 12 and 15, except that
10 a so-called "perpendicular double layered medium" was formed by forming a FeAlSi soft magnetic layer between the nonmagnetic substrate and the first under layer. The magnetic characteristics of each of the resultant perpendicular double layer media were evaluated, and
15 the characteristics of the recording layer alone were evaluated by separating the FeAlSi soft magnetic layer, so as to obtain the results substantially equal to those of Examples 1 to 12 and 15. In other words, the characteristics as the perpendicular magnetic recording
20 medium were found to have been improved, compared with Comparative Examples 1 to 14. Such being the situation, it has been clarified that the effect of the FeAlSi soft magnetic layer of the laminate structure can be maintained even where the FeAlSi layer is
25 formed to form a perpendicular double layer medium, making it possible to improve the perpendicular orientation, the perpendicular coercive force and the

reproducing output of the perpendicular magnetic recording medium.

Example 17:

Perpendicular magnetic recording media were
5 prepared as in Examples 1 to 12 and 15, except that a
so-called "perpendicular double layered medium" was
formed by forming a FeTaC soft magnetic layer between
the nonmagnetic substrate and the first under layer.
The magnetic characteristics of each of the resultant
10 perpendicular double layer media were evaluated, and
the characteristics of the recording layer alone were
evaluated by separating the FeTaC soft magnetic layer,
so as to obtain the results substantially equal to
those of Examples 1 to 12 and 15. In other words, the
15 characteristics as the perpendicular magnetic recording
medium were found to have been improved, compared
with Comparative Examples 1 to 14. Such being the
situation, it has been clarified that the effect of
the under layer of the laminate structure can be
20 maintained even where the FeTaC layer is formed to
form a perpendicular double layer medium, making it
possible to improve the perpendicular orientation,
the perpendicular coercive force and the reproducing
output of the perpendicular magnetic recording medium.

25 Example 18:

Perpendicular magnetic recording media were
prepared as in Examples 1 to 12 and 15, except that

a so-called "perpendicular double layered medium" was formed by forming a FeZrN soft magnetic layer between the nonmagnetic substrate and the first under layer. The magnetic characteristics of each of the resultant perpendicular double layer media were evaluated, and the characteristics of the recording layer alone were evaluated by separating the FeZrN soft magnetic layer, so as to obtain the results substantially equal to those of Examples 1 to 12 and 15. In other words, the characteristics as the perpendicular magnetic recording medium were found to have been improved, compared with Comparative Examples 1 to 14. Such being the situation, it has been clarified that the effect of the under layer of the laminate structure can be maintained even where the FeZrN layer is formed to form a perpendicular double layer medium, making it possible to improve the perpendicular orientation, the perpendicular coercive force and the reproducing output of the perpendicular magnetic recording medium.

Example 19:

Perpendicular magnetic recording media were prepared as in Examples 1 to 12 and 15, except that a so-called "perpendicular double layered medium" was formed by forming a FeCo soft magnetic layer between the nonmagnetic substrate and the first under layer. The magnetic characteristics of each of the resultant perpendicular double layer media were evaluated, and

the characteristics of the recording layer alone were evaluated by separating the FeCo soft magnetic layer, so as to obtain the results substantially equal to those of Examples 1 to 12 and 15. In other words, the characteristics as the perpendicular magnetic recording medium were found to have been improved, compared with Comparative Examples 1 to 14. Such being the situation, it has been clarified that the effect of the under layer of the laminate structure can be maintained even where the FeCo layer is formed to form a perpendicular double layer medium, making it possible to improve the perpendicular orientation, the perpendicular coercive force and the reproducing output of the perpendicular magnetic recording medium.

Example 20:

Perpendicular magnetic recording media were prepared as in Examples 1 to 15, except that a so-called "perpendicular double layer medium" was formed by forming a CoZrNb soft magnetic layer between the nonmagnetic substrate and the first under layer. The magnetic characteristics of each of the resultant perpendicular double layer media were evaluated, and the characteristics of the recording layer alone were evaluated by separating the CoZrNb soft magnetic layer, so as to obtain the results substantially equal to those of Examples 1 to 12 and 15. In other words, the characteristics as the perpendicular magnetic recording

medium were found to have been improved, compared with Comparative Examples 1 to 14. Such being the situation, it has been clarified that the effect of the under layer of the laminate structure can be maintained even where the CoZrNb layer is formed to form a perpendicular double layer medium, making it possible to improve the perpendicular orientation, the perpendicular coercive force and the reproducing output of the perpendicular magnetic recording medium.

It should be noted that the materials of the soft magnetic layer are not limited to those used in the Examples of the present invention described above. Particularly, it was found possible to obtain the similar effect by using the other soft magnetic materials in the case of forming an amorphous layer such as a carbon layer on the soft magnetic layer.

FIG. 4 shows an example of the magnetic recording apparatus in which the perpendicular magnetic recording media according to the first to sixth aspects of the present invention can be applied. As shown in the drawing, a magnetic disc 121 of a hard structure for recording information is mounted to a spindle 122 and is rotated at a predetermined speed by a spindle motor (not shown). A slider 123 has a magnetic head is provided on the tip of a suspension 124 formed in a thin plate-like leaf spring which access to the magnetic disc 121 to read and write signals.

The suspension 124 is connected to one end portion of an arm 125 having a bobbin etc. for holding a driving coil (not shown).

5 A voice coil motor 126, which is a kind of a linear motor, is mounted on the other end portion of the arm 125. The voice coil motor 126 comprises a driving coil (not shown) wound up to the bobbin portion of the arm 125 and a magnetic circuit consisting of a permanent magnet arranged to have the driving coil held
10 therein and a yoke positioned to face the permanent magnet.

The arm 125 is held by ball bearings mounted in the upper and lower portions of a stationary shaft 127 so as to be rotated and swung by the voice coil motor
15 126. In other words, the position of the slider 123 on the magnetic disc 121 is controlled by the voice coil motor 126. Incidentally, a reference numeral 128 in FIG. 4 denotes a lid.

The perpendicular magnetic recording media
20 according to the first to sixth aspects of the present invention have good perpendicular orientation and perpendicular coercive force in the recording layer thereof. Therefore a hard disk device exhibiting high density and high read output can be realized by using
25 one of such media.

Additional advantages and modifications will readily occur to those skilled in the art. Therefore,

the invention in its broader aspects is not limited to the specific details and representative embodiments shown and described herein. Accordingly, various modifications may be made without departing from the spirit or scope of the general inventive concept as
5 defined by the appended claims and their equivalents.

10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
66
67
68
69
70
71
72
73
74
75
76
77
78
79
80
81
82
83
84
85
86
87
88
89
90
91
92
93
94
95
96
97
98
99
100
101
102
103
104
105
106
107
108
109
110
111
112
113
114
115
116
117
118
119
120
121
122
123
124
125
126
127
128
129
130
131
132
133
134
135
136
137
138
139
140
141
142
143
144
145
146
147
148
149
150
151
152
153
154
155
156
157
158
159
160
161
162
163
164
165
166
167
168
169
170
171
172
173
174
175
176
177
178
179
180
181
182
183
184
185
186
187
188
189
190
191
192
193
194
195
196
197
198
199
200
201
202
203
204
205
206
207
208
209
210
211
212
213
214
215
216
217
218
219
220
221
222
223
224
225
226
227
228
229
230
231
232
233
234
235
236
237
238
239
240
241
242
243
244
245
246
247
248
249
250
251
252
253
254
255
256
257
258
259
260
261
262
263
264
265
266
267
268
269
270
271
272
273
274
275
276
277
278
279
280
281
282
283
284
285
286
287
288
289
290
291
292
293
294
295
296
297
298
299
300
301
302
303
304
305
306
307
308
309
310
311
312
313
314
315
316
317
318
319
320
321
322
323
324
325
326
327
328
329
330
331
332
333
334
335
336
337
338
339
340
341
342
343
344
345
346
347
348
349
350
351
352
353
354
355
356
357
358
359
360
361
362
363
364
365
366
367
368
369
370
371
372
373
374
375
376
377
378
379
380
381
382
383
384
385
386
387
388
389
390
391
392
393
394
395
396
397
398
399
400
401
402
403
404
405
406
407
408
409
410
411
412
413
414
415
416
417
418
419
420
421
422
423
424
425
426
427
428
429
430
431
432
433
434
435
436
437
438
439
440
441
442
443
444
445
446
447
448
449
450
451
452
453
454
455
456
457
458
459
460
461
462
463
464
465
466
467
468
469
470
471
472
473
474
475
476
477
478
479
480
481
482
483
484
485
486
487
488
489
490
491
492
493
494
495
496
497
498
499
500
501
502
503
504
505
506
507
508
509
510
511
512
513
514
515
516
517
518
519
520
521
522
523
524
525
526
527
528
529
530
531
532
533
534
535
536
537
538
539
540
541
542
543
544
545
546
547
548
549
550
551
552
553
554
555
556
557
558
559
560
561
562
563
564
565
566
567
568
569
570
571
572
573
574
575
576
577
578
579
580
581
582
583
584
585
586
587
588
589
590
591
592
593
594
595
596
597
598
599
600
601
602
603
604
605
606
607
608
609
610
611
612
613
614
615
616
617
618
619
620
621
622
623
624
625
626
627
628
629
630
631
632
633
634
635
636
637
638
639
640
641
642
643
644
645
646
647
648
649
650
651
652
653
654
655
656
657
658
659
660
661
662
663
664
665
666
667
668
669
670
671
672
673
674
675
676
677
678
679
680
681
682
683
684
685
686
687
688
689
690
691
692
693
694
695
696
697
698
699
700
701
702
703
704
705
706
707
708
709
710
711
712
713
714
715
716
717
718
719
720
721
722
723
724
725
726
727
728
729
730
731
732
733
734
735
736
737
738
739
740
741
742
743
744
745
746
747
748
749
750
751
752
753
754
755
756
757
758
759
760
761
762
763
764
765
766
767
768
769
770
771
772
773
774
775
776
777
778
779
780
781
782
783
784
785
786
787
788
789
790
791
792
793
794
795
796
797
798
799
800
801
802
803
804
805
806
807
808
809
810
811
812
813
814
815
816
817
818
819
820
821
822
823
824
825
826
827
828
829
830
831
832
833
834
835
836
837
838
839
840
841
842
843
844
845
846
847
848
849
850
851
852
853
854
855
856
857
858
859
860
861
862
863
864
865
866
867
868
869
870
871
872
873
874
875
876
877
878
879
880
881
882
883
884
885
886
887
888
889
890
891
892
893
894
895
896
897
898
899
900
901
902
903
904
905
906
907
908
909
910
911
912
913
914
915
916
917
918
919
920
921
922
923
924
925
926
927
928
929
930
931
932
933
934
935
936
937
938
939
940
941
942
943
944
945
946
947
948
949
950
951
952
953
954
955
956
957
958
959
960
961
962
963
964
965
966
967
968
969
970
971
972
973
974
975
976
977
978
979
980
981
982
983
984
985
986
987
988
989
990
991
992
993
994
995
996
997
998
999
1000
1001
1002
1003
1004
1005
1006
1007
1008
1009
1010
1011
1012
1013
1014
1015
1016
1017
1018
1019
1020
1021
1022
1023
1024
1025
1026
1027
1028
1029
1030
1031
1032
1033
1034
1035
1036
1037
1038
1039
1040
1041
1042
1043
1044
1045
1046
1047
1048
1049
1050
1051
1052
1053
1054
1055
1056
1057
1058
1059
1060
1061
1062
1063
1064
1065
1066
1067
1068
1069
1070
1071
1072
1073
1074
1075
1076
1077
1078
1079
1080
1081
1082
1083
1084
1085
1086
1087
1088
1089
1090
1091
1092
1093
1094
1095
1096
1097
1098
1099
1100
1101
1102
1103
1104
1105
1106
1107
1108
1109
1110
1111
1112
1113
1114
1115
1116
1117
1118
1119
1120
1121
1122
1123
1124
1125
1126
1127
1128
1129
1130
1131
1132
1133
1134
1135
1136
1137
1138
1139
1140
1141
1142
1143
1144
1145
1146
1147
1148
1149
1150
1151
1152
1153
1154
1155
1156
1157
1158
1159
1160
1161
1162
1163
1164
1165
1166
1167
1168
1169
1170
1171
1172
1173
1174
1175
1176
1177
1178
1179
1180
1181
1182
1183
1184
1185
1186
1187
1188
1189
1190
1191
1192
1193
1194
1195
1196
1197
1198
1199
1200
1201
1202
1203
1204
1205
1206
1207
1208
1209
1210
1211
1212
1213
1214
1215
1216
1217
1218
1219
1220
1221
1222
1223
1224
1225
1226
1227
1228
1229
1230
1231
1232
1233
1234
1235
1236
1237
1238
1239
1240
1241
1242
1243
1244
1245
1246
1247
1248
1249
1250
1251
1252
1253
1254
1255
1256
1257
1258
1259
1260
1261
1262
1263
1264
1265
1266
1267
1268
1269
1270
1271
1272
1273
1274
1275
1276
1277
1278
1279
1280
1281
1282
1283
1284
1285
1286
1287
1288
1289
1290
1291
1292
1293
1294
1295
1296
1297
1298
1299
1300
1301
1302
1303
1304
1305
1306
1307
1308
1309
1310
1311
1312
1313
1314
1315
1316
1317
1318
1319
1320
1321
1322
1323
1324
1325
1326
1327
1328
1329
1330
1331
1332
1333
1334
1335
1336
1337
1338
1339
1340
1341
1342
1343
1344
1345
1346
1347
1348
1349
1350
1351
1352
1353
1354
1355
1356
1357
1358
1359
1360
1361
1362
1363
1364
1365
1366
1367
1368
1369
1370
1371
1372
1373
1374
1375
1376
1377
1378
1379
1380
1381
1382
1383
1384
1385
1386
1387
1388
1389
1390
1391
1392
1393
1394
1395
1396
1397
1398
1399
1400
1401
1402
1403
1404
1405
1406
1407
1408
1409
1410
1411
1412
1413
1414
1415
1416
1417
1418
1419
1420
1421
1422
1423
1424
1425
1426
1427
1428
1429
1430
1431
1432
1433
1434
1435
1436
1437
1438
1439
1440
1441
1442
1443
1444
1445
1446
1447
1448
1449
1450
1451
1452
1453
1454
1455
1456
1457
1458
1459
1460
1461
1462
1463
1464
1465
1466
1467
1468
1469
1470
1471
1472
1473
1474
1475
1476
1477
1478
1479
1480
1481
1482
1483
1484
1485
1486
1487
1488
1489
1490
1491
1492
1493
1494
1495
1496
1497
1498
1499
1500
1501
1502
1503
1504
1505
1506
1507
1508
1509
1510
1511
1512
1513
1514
1515
1516
1517
1518
1519
1520
1521
1522
1523
1524
1525
1526
1527
1528
1529
1530
1531
1532
1533
1534
1535
1536
1537
1538
1539
1540
1541
1542
1543
1544
1545
1546
1547
1548
1549
1550
1551
1552
1553
1554
1555
1556
1557
1558
1559
1560
1561
1562
1563
1564
1565
1566
1567
1568
1569
1570
1571
1572
1573
1574
1575
1576
1577
1578
1579
1580
1581
1582
1583
1584
1585
1586
1587
1588
1589
1590
1591
1592
1593
1594
1595
1596
1597
1598
1599
1600
1601
1602
1603
1604
1605
1606
1607
1608
1609
1610
1611
1612
1613
1614
1615
1616
1617
1618
1619
1620
1621
1622
1623
1624
1625
1626
1627
1628
1629
1630
1631
1632
1633
1634
1635
1636
1637
1638
1639
1640
1641
1642
1643
1644
1645
1646
1647
1648
1649
1650
1651
1652
1653
1654
1655
1656
1657
1658
1659
1660
1661
1662
1663
1664
1665
1666
1667
1668
1669
1670
1671
1672
1673
1674
1675
1676
1677
1678
1679
1680
1681
1682
1683
1684
1685
1686
1687
1688
1689
1690
1691
1692
1693
1694
1695
1696
1697
1698
1699
1700
1701
1702
1703
1704
1705
1706
1707
1708
1709
1710
1711
1712
1713
1714
1715
1716
1717
1718
1719
1720
1721
1722
1723
1724
1725
1726
1727
1728
1729
1730
1731
1732
1733
1734
1735
1736
1737
1738
1739
1740
1741
1742
1743
1744
1745
1746
1747
1748
1749
1750
1751
1752
1753
1754
1755
1756
1757
1758
1759
1760
1761
1762
1763
1764
1765
1766
1767
1768
1769
1770
1771
1772
1773
1774
1775
1776
1777
1778
1779
1780
1781
1782
1783
1784
1785
1786
1787
1788
1789
1790
1791
1792
1793
1794
1795
1796
1797
1798
1799
1800
1801
1802
1803
1804
1805
1806
1807
1808
1809
1810
1811
1812
1813
1814
1815
1816
1817
1818
1819
1820
1821
1822
1823
1824
1825
1826
1827
1828
1829
1830
1831
1832
1833
1834
1835
1836
1837
1838
1839
1840
1841
1842
1843
1844
1845
1846
1847
1848
1849
1850
1851
1852
1853
1854
1855
1856
1857
1858
1859
1860
1861
1862
1863
1864
1865
1866
1867
1868
1869
1870
1871
1872
1873
1874
1875
1876
1877
1878
1879
1880
1881
1882
1883
1884
1885
1886
1887
1888
1889
1890
1891
1892
1893
1894
1895
1896
1897
1898
1899
1900
1901
1902
1903
1904
1905
1906
1907
1908
1909
1910
1911
1912
1913
1914
1915
1916
1917
1918
1919
1920
1921
1922
1923
1924
1925
1926
1927
1928
1929
1930
1931
1932
1933
1934
1935
1936
1937
1938
1939
1940
1941
1942
1943
1944
1945
1946
1947
1948
1949
1950
1951
1952
1953
1954
1955
1956
1957
1958
1959
1960
1961
1962
1963
1964
1965
1966
1967
1968
1969
1970
1971
1972
1973
1974
1975
1976
1977
1978
1979
1980
1981
1982
1983
1984
1985
1986
1987
1988
1989
1990
1991
1992
1993
1994
1995
1996
1997
1998
1999
2000
2001
2002
2003
2004
2005
2006
2007
2008
2009
2010
2011
2012
2013
2014
2015
2016
2017
2018
2019
2020
2021
2022
2023
2024
2025
2026
2027
2028
2029
2030
2031
2032
2033
2034
2035
2036
2037
2038
2039
2040
2041
2042
2043
2044
2045
2046
2047
2048
2049
2050
2051
2052
2053
2054
2055
2056
2057
2058
2059
2060
2061
2062
2063
2064
2065
2066
2067
2068
2069
2070
2071
2072
2073
2074
2075
2076
2077
2078
2079
2080
2081
2082
2083
2084
2085
2086
2087
2088
2089
2090
2091
2092
2093
2094
2095
2096
2097
2098
2099
2100
2101
2102
2103
2104
2105
2106
2107
2108
2109
2110
2111
2112
2113
2114
2115
2116
2117
2118
2119
2120
2121
2122
2123
2124
2125
2126
2127
2128
2129
2130
2131
2132
2133
2134
2135
2136
2137
2138
2139
2140
2141
2142
2143
2144
2145
2146
2147
2148
2149
2150
2151
2152
2153
2154
2155
2156
2157
2158
2159
2160
2161
2162
2163
2164
2165
2166
2167
2168
2169
2170
2171
2172
2173
2174
2175
2176
2177
2178
2179
2180
2181
2182
2183
2184
2185
2186
2187
2188
2189
2190
2191
2192
2193
2194
2195
2196
2197
2198
2199
2200
2201
2202
2203
2204
2205
2206
2207
2208
2209
2210
2211
2212
2213
2214
2215
2216
2217
2218
2219
2220
2221
2222
2223
2224
2225
2226
2227
2228